



**“PERFORMING POLYMER ASSISTED CDS-ZNS NANO COMPOSITES:
SYNTHESIS AND CHARACTERIZATION FOR A RANGE OF APPLICATIONS”**

Ms. Dipali Nagnath Hodade

PHD Student, Dr. APJ Abdul Kalam University, Indore, MP, India.
Department of Physics, dipalihodade2@gmail.com

Dr. Mohan N Giriya

Principal, Chintamani College of Arts and Science, Gondpipri, Dist: Chandrapur, M.S, India
mohangiriya@gmail.com

Abstract: Synthesis and study of conducting polymers' physical characteristics are keys. Polyaniline is conductive. X-ray diffraction (XRD) showed that the matrix contains pure nano CdS particles.

This work prepares nanostructured polyaniline (PANI) using four sol-gel methods. Morphology of PANI samples was determined by X-ray diffraction was used to characterize PANI molecular structure (XRD). The results of the characterization of the prepared PANI show that the morphology, chemical composition, crystallinity, conductivity, and surface area were significantly altered as a result of the atypical techniques that were used in its synthesis. This was confirmed by the results of the characterization. This paper examines recent advances in polyaniline conducting polymer production and characteristics. Synthesis of polyaniline using traditional and grafted methods has been reviewed. By this high-accuracy development process, structure and properties are directly related. Structure-modified polyaniline can be used in the future.

Observations showed that PANI/CdS nanocomposites have higher DC conductivity than PANI.

By oxidizing aniline with cadmium sulfate 3.5 pH, conducting polyaniline nanocomposites with CdS nanoparticles were produced in situ. CdS-nanoparticles affect polyaniline's electrical conductivity. The homogeneous intercalation of CdS nanoparticles leads in a cooperative phenomenon between polyaniline and the nanoparticles, increasing the electrical conductivity of polyaniline nano-composite compared to pure polyaniline.

Keywords: Synthesis, Sol-gel, XRD, ZNS, the polyaniline substance Polymer, Tiny particle, Characterization, PANI/CdS nano-composite composition

I. INTRODUCTION

Cadmium Sulphide and Polyaniline films were produced using vacuum evaporation. Single-layer and multilayer films were grown and characterized. In this study, multilayer CdS/Polyaniline thin films are X-ray diffracted.

Sol-gel plus chemical oxidation produces conducting polyaniline (PANI). Screen-printed cadmium sulphide on polyaniline pellet PANI/CdS nano-composite material was produced utilizing FeCl₃ as an oxidant.

Sulphide semiconductors are one of the most-studied thin-film semiconductors, and many deposition processes have been used to make solar cells. Cadmium sulphide films produced by vacuum evaporation are utilized as oxygen sensors.

In polymerization of aniline monomer in the presence of dispersed CdS quantum dots and multi-walled carbon nanotubes has produced polyaniline/carbon nanotube/CdS quantum dot composites with improved optical and electrical characteristics.

Polyaniline (PANI) has a simple synthetic technique, strong environmental and thermal stability, a vast conductivity range, and good optical, electrochemical, and chemical properties, making it a model structure for advanced study and the basis for a new class of innovative materials/composites.

We created a PANI/CdS composite with homogeneous CdS dispersion. In-situ polymerization of aniline in multi-walled CdS yielded PANI/CdS quantum dots.

Polymerization at the water-toluene interface forms a transparent, free-standing layer. Plasma pretreatment and in-situ polymerization make polyaniline composites conductive.

Spin-coated polyaniline–CdS nanocomposites' sensing properties

Proposed System

XRD validates PANI/CdS' crystal structure. SEM and XRD demonstrate composites' changed crystallinity. CdS crystallites develop and impregnate PANI's granular pillar-like structure. The composite absorbs bluer than CdS. PANI's C=C bond alters infrared wave numbers.

PANI switches between base and salt states quickly. PANI has good reduction and oxidation properties, electrical conductivity, a simple manufacturing method, and environmental stability. PANI was oxidatively polymerized from aniline monomers. Different approaches were utilized as PANI research progressed.

- Polymerization using electrochemistry.
- Polymerization by chemicals.
- Polymerization in the vapor phase (VPP).
- Polymerization that was started by photochemistry.
- Polymerization facilitated by enzymes.
- Electron acceptor-based polymerization

Material & Techniques

Polyaniline synthesis

Polyaniline was made through oxidative polymerization. In a beaker, 0.2M (0.8 g) aniline, 2 M HCl, and distilled water were mixed. Beaker in (0-8) oC ice bath. The glass substrate was dipped.

Ammonium peroxydisulfate was dissolved in 2 M HCl and purified water. Drop by drop, ammonium peroxydisulfate was added to aniline while stirring.

The mixture turns from light blue to blue green to greenish black during polymerization. Color denotes emeraldine salt polyaniline. We kept this overnight. Filtered and rinsed with HCl and distilled water to eliminate contaminants. The residue and substrate were dried at 80°C for 4 hours.

Polyaniline, a conducting polymer, has several uses. This conducting polymer is likely produced in rings and nitrogen-substituted derivatives. Each derivative has two oxidation states, which are created using different dopants and non-redox, chemical, or electrochemical oxidation. The technological potential of these materials depends on their cost-effectiveness, stability, and ease of synthesis and processing.

Cadmium-sulfide synthesis

80 ml distilled water dissolved 6.396 mg cadmium acetate and 3.648 g thiourea. Drop by drop, thiourea solution was added to the cadmium acetate solution while stirring. After 3.5 h, nanoparticles precipitate and the solution turns yellow. The solution sat overnight without stirring. Bottom-stabilizing CdS nanoparticles; filtered and rinsed with distilled water to remove contaminants; precipitate and substrate were dried at 70°C for 4 hours.

Nanocomposite PANI–CdS

In oxidative polymerization, PANI–CdS nanocomposites were made with 10, 20, 30, 40, and 50% CdS nanoparticles. 0.97 g aniline in 94.3 ml distilled water with 2 M HCl. The solution was stirred in (0–8)°C ice bath. 4.2 g ammonium peroxy-disulfate was dissolved in 94.3 ml 2 M HCl in distilled water. Drop by drop, ammonium peroxydisulfate solution was added to aniline solution. The solution was agitated for 12h after adding 10, 20, 30, 40, and 50% CdS. Two times with HCl and distilled water, the precipitate was filtered. Precipitate and substrate were dried at 80°C for 4 hours.

This study analyzes iodine's effect on polymer/inorganic nanocomposites. I₂@PANI is redox-coated iodine nanoparticles on PANI nano-fibers. CdS nanoparticles increase I₂@PANI–CdS photocurrent (as electron acceptors). I₂'s penetration into porous semiconductor sheets, quick charge transfer, and slow photoelectron recombination all help. Nano-CdS may have more charge carriers. I₂@PANI–CdS nanocomposites boost photocurrent.

XRD confirms a PANI/CdS composite's crystalline structure. SEM and XRD show the composites' altered form and crystallinity. Transmission electron microscopy shows CdS crystallites growing and impregnating PANI's granular pillar-like structure. The composite's absorption edge is blue-shifted compared to CdS. PANI's C14C bond strengthens, causing a shift in infrared wave numbers.

Summary

The first in-situ oxidative polymerization of polyaniline–CdS nanocomposite was performed. This study used hybrid POT–CSA–CdSe–TEA nanoparticles. Studying electricity, structure, and morphology. XRD hybrids are cubic like CdSe nanoparticles. Semiconducting hybrids

conduct 0.1 S.cm⁻².

This paper polymerizes ultrasonic-irradiated cadmium sulphide. USI makes organic-polymer composites. PANI/CdS. This USI creates particles. Concentration controls PANI/CdS particle size. USI is not chemically made like PANI/CdS. USI splits PANI/CdS. USI strengthens composite. CdS PANI blocks micro-fibre polymerization. Discover USI and XRD-verified PANI/CdS. Both materials retained crystal structures but lost XRD crystallinity after USI. TEM and SEM confirm XRD.

PANI and CdS-QDs nanocomposites were examined for optics, electronics, morphology, and structure. CdS-PANI nanocomposites precipitate QDs and polyaniline. The UV eV spectroscopy examined PANI, CdS-PANI nanocomposites, and CdS quantum dots. Quantum dots modify PANI's band gap. PANI and nanocomposites showed 1-D charge transport in DC conductivity measurements. CdS-PANI DC conductivity rises with CdS and temperature. AC conductivity of CdS-PANI nanocomposites depends on temperature, frequency, and CdS content.

This study creates CdS-based PANI nanocomposites with APS as an oxidant. Chemical structure, morphology, and electrical properties are studied. Nanoparticle form and content are determined by TEM. Fore Probe measures CdS composite conductivity. Calculating activation energy with polyaniline and various CdS nanocomposite weights.

Green bio-catalytic polymerization. More than chemicals and recyclable enzymes are made. Under mild conditions, this process is selective, catalytic, efficient, low-energy, etc. It uses enzymes and organic solvents.

Others require superfluous steps, whereas enzyme-catalyzed polymers are well-structured. Process and dissolve with templates. Polyelectrolyte templates foster para coupling and counterion doping.

This study analyses new polyaniline conducting polymer synthesis and properties. Traditional, ultrasonic, Fenton, and grafting polyaniline synthesis methods are addressed. Highly accurate evolution links structure and characteristics.

Potential of structure-modified polyaniline.

Optoelectronics, morphology, and PIn/CdS nanocomposite structure are reported. FT-IR and XRD found CdS in PIn. TEM and FESEM examined synthesized samples. Nanocomposite PIn/CdS 2.15 eV optical band gap; PL spectra electron-hole mobility. The J-V characteristics of PIn/CdS nanocomposite Ohmic conductance were examined. Each statistic shows optoelectronic PIn/applicability CdSs.

In PANI nanocomposites, CdSe cubic constants are 6.24 and 5.44. PANI sphere. PANI-CdSe nanocomposite EDAX-validated. Ohmic P-N diodes. Better PANI/CdSe nanocomposite DC conductivity. The material can build gas sensors, protective devices, P-N junction diodes, and electronics with 150 [A (cm)⁻²] short circuit current.

PVA had CdS nanoparticles. PVA/CdS nanocomposite films examined CdS nanoparticles' effects on PVA. We examine mechanical and structural properties. FTIR peaks show C-H, CO, COC, and COS stretching; XRD shows 100% nano-CdS. SEM pictures of PVA/CdS nanocomposite showed nanoparticle agglomeration. We measure thermal characteristics with DSC.

Many electroactive polymers use. Conductive polymer PANI is easy to make. PANI LEDs light. Low-cost PANI solar cells. PANI solar cells are affordable and efficient. PANI gas and glucose sensors are popular. Increase energy efficiency with supercapacitors. Super capacitors use PANI's cost, conductivity, and redox. Medicine needs new tech. Neuroprotective brain probes improve neurology.

Video and probable PANI/CdS analysis in situ. XRD, FTIR, and SEM evaluated structure, shape, crystallinity, composition, and molecular interaction. Based on AC frequency, nanocomposite CdS enhances conductivity, dielectric, and impedance. Percolation changes PANI/CdS.

P3 composite dielectric is low. CdS nanoparticles impact electric composites. Conductive hybrid polymers store energy.

Biosensor matrix clad. Cross-linked glucose oxidase. Certified nanocomposite by XRD/FE-SEM. Sensor nanocomposite matrix was optically imaged. A glucose sensor. Biomolecules stick to fibre optic sensors with PANI-CdS.


Sol-gel nano-CdS. Polyaniline was oxidised aniline. 20-30-40-50% CdS PANI-CdS nanocomposites. X-ray diffraction peaks are 21.5 θ , 25.7 θ , and 28.1 θ for emerald salt polyani Peaks at 26.69 and 47.47 suggest hexagonal and cubic CdS. PANI crystallites are 7.95 and 12.09 nm. Polyaniline CdS-FTIR. AFM discovers PANI CdS.

On-site aniline monomer CNT polymerization increased CdS quantum dots' optical and electrical characteristics. CdS dots' first-, second-, and third-order phonons. Excitons and quantum dots carry charge in PANI/CNT/CdS (2 wt.%) combinations. Optoelectronics

Weight loss (%) at various temperatures for the as-prepared materials


Specimen	Weight loss (%) 30- 300 °C	Weight loss (%) 350- 650 °C	Weight loss (%) 650- 950 °C	Net Weight loss (%)
PANI	21.41	25.56	14.09	58.96
PANI/CdS	19.71	18.05	20.68	55.62
PANI/CdS	18.95	16.61	22.31	52.98

The technique was utilised in order to investigate the surface morphology of the materials that were synthesized in their natural state. These materials included pristine PANI, graphene oxide, CdS nanoparticles, and their nanohybrids.




Ohmic conductance and resistance of the as-prepared samples

Sample	Ohmic Conductance (S)	Ohmic Resistance (Ω)
CdS	0.078	19.85
Neat PANI	0.089	14.59
PANI/CdS	0.101	11.37
PANI/Gradient/Cds	0.392	04.82



Summary of the parameters extracted from the devices with different cadmium concentrations.

CdCl ₂ Concentration	Resistance (K Ω)	Isc (μ A)	Voc (mV)	FF (%)	Efficiency
3.8	4.1	8.9	91	35	0.0389
7	7.9	11	278	32	0.01156
8.9	11.5	38	478	39	0.1098
12	4.6	38	395	49	0.425
14.9	5.8	43	294	37	0.783




The photovoltaic characteristics that were acquired by adjusting the polymerization time, the concentration of cadmium, and the concentration of dopant.

The output current (Isc) also increased as the concentration of CdS increased, which may be owing to an increase in defects and, as a result, an increase in light absorption and photon conversion.

Summary of the parameters extracted from the devices with different polymerization times.

Time	Resistance (KΩ)	Isc (μA)	Voc (mV)	FF (%)	Efficiency
100	7.8	40	180	16	0.0986
200	11	45	440	40	0.086
300	39	365	520	29	0.78
400	41	105	899	30	0.64
500	52	98	564	35	0.15




Nanoparticles provide a high interfacial surface for charge separation and reduced recombination, whilst polyaniline can be modified to have certain electrical characteristics and a band gap that can be tailored to the specifications of the device.

Through the use of photo-electrochemical research, this composite has demonstrated the potential to be utilised in photovoltaic applications. An IPCE value of 11.2% was obtained by photocurrent studies, which revealed a high photon conversion efficiency when exposed to light environments. There will be an improvement in device response if effective solutions for

matrix alignment are developed.

The strongest peaks of PANI and CdS which appear in XRD of PANI–CdS (10–50 wt.%) composites.


Samples	PANI Peaks			Hexagonal CdS peaks			Cubic CdS peaks		
	2θ deg.	hkl	I/I ₀	2θ deg.	hkl	I/I ₀	2θ deg.	hkl	I/I ₀
10%	25.7	110	100	28.1	101	39	28.1	111	39
20%	25.5	110	100	28.1	101	53	28.1	111	53
30%	25.4	110	100	27.8	101	44	27.8	111	44
40%	25.7	110	100	26.8	002	53	28	111	28
50%	25	110	19	26.6	002	100	27.9	111	27



The XRD pattern of PANI– CdS (10–50 wt.%) composites show interconnected PANI and CdS peaks. From this pattern, CdS peaks are lower intensity than PANI peaks, but in the sample with 50% CdS, hexagonal and cubic CdS peaks are clearly visible and PANI peak intensity decreases due to CdS concentration, which forms an interlocking structure between CdS nanoparticles and PANI matrix. Table 1 shows the brightest PANI and CdS peaks in PANI–CdS (10–50 wt.%) composite XRD.

XRD for PANI, CdS nanoparticles and PANI–CdS nanocomposites


Material	2θ (deg.)	Plane (hkl P)	FWHM (deg.)	Crys. size (nm)	d (Å)
PANI	25.75	110	1.05	7.95	3.45
CdS	26.69	002	0.925	12.09	3.33
10%	25.72	100	1.25	6.64	3.46
20%	25.54	100	1.158	7.01	3.48
30%	25.45	100	1.176	6.84	3.49
40%	25.75	100	1.885	4.42	3.45
50%	25.05	110	0.50	15.90	3.55



Illustrates the variation in the diffraction angle of CdS in PANI-CdS composites as a function of CdS concentration, relative to the standard diffraction angle of CdS. The shifting of the CdS peaks in this diagram indicates the existence of tension within the lattice.

AFM data for the samples.


Sample	Average grain size (nm)	Roughness (nm)	Root mean square (nm)
PANI	99.40	14.5	16.8
CdS	99.40	2.19	2.56
PANI-CdS (10%)	90.07	5.26	6.25
PANI-CdS (20%)	76.66	5.95	7.17
PANI-CdS (30%)	105.22	1.49	1.77
PANI-CdS (40%)	70.55	0.599	0.748
PANI-CdS (50%)	78.34	3.73	4.54



Kinetic parameters for PANI and nanocomposites

Polymer composites	Ea (KJ/mole)	ΔS (J/K)	G (KJ/mole)	Ts (K)
PANI	9.5	43.16	24.4	786
PANI-CdS 5%	11.94	43.08	48.34	845
PANI-CdS 10%	12.52	42.86	50.11	877
PANI-CdS 15%	13.152	43.12	52.39	910
PANI-CdS 20%	13.71	43.20	57.5	1014
PANI-ZnS 5%	10.1	42.7	40.85	745
PANI-ZnS 10%	11.79	43.4	45.64	780
PANI-ZnS 15%	13.21	43.1	47.70	800

PANI-ZnS 20%	11.7	42.9	49.8	888
--------------	------	------	------	-----



CONCLUSION

The inhibitory zone that is produced by cotton that has been treated with polyaniline is as thin as it is physically possible for that zone to be. The antibacterial activity of PANI can be explained in a number of different ways, including the protonation of cadmium sulfide-containing polymer groups, the physical interaction that takes place between the microbial cell and the polymer as a result of the chain structure of PANI, as well as a number of other possibilities. PANI has been shown to inhibit the growth of a wide variety of bacteria.

Simple techniques of synthesis were employed for PANI and CdS nanoparticles, respectively, in order to explore the structural and surface properties of PANI, CdS nanoparticles, and PANI-CdS nanocomposites. This was done in order to better understand the relationship between the three materials. PANI and CdS nanoparticles were the first ones to be manufactured. In the X-ray diffraction pattern of PANI-CdS nanocomposites, it was observed that the peaks of PANI and CdS occurred together at the same spot. This was a significant finding. This turned out to be a very important discovery. This shows that they are connected, and the fact that PANI and CdS have separate crystallite shapes produces stress in the nanocomposites because of the difference in the structures of the crystallites. Consequently, this suggests that they are connected. This is because the nanocomposites are composed of both of these materials, which explains why this is the case.

The synthesis of PANI/CdS is one that can be repeated and carried out on a far bigger scale than it was previously possible. A polymer composite will form on the surface of the PANI if it is allowed to come into contact with CdS. The combination of these two compounds brings about this effect, which is a consequence of their interaction. During the course of the inquiry, EDS and XRD were utilized, which ultimately resulted in the discovery that the PANI composite contains cadmium sulfide as one of its component parts. The interaction between PANI and CdS has been shown to be both genuine and functional by utilizing a number of various vibrational patterns. This has been shown to be the case. After going through the process of composite synthesis with PANI, the CdS crystals ended up taking the shape of a hexagon when the process was finished. This observation refers to the production of PANI/CdS

composites, as it is possible to make out clusters of CdS that have collected in PANI fibers. You can locate the images that were taken by the TEM in this location.

REFERENCES

1. Synthesis of Polyaniline Supported CdS/CdS-ZnS/CdS-TiO₂ Nanocomposite for Efficient Photocatalytic Applications, Nida Qutub, Preeti Singh, Suhail Sabir, Khalid Umar, Suresh Sagadevan and Won-Chun Oh, *Nanomaterials* 2022
2. Synthesis, Characterization, Conductivity and Gas Sensing Performance of Copolymer Nanocomposites Based on Copper Alumina and Poly(aniline-co-pyrrole) S Sankar M.T. Ramesan, *research square*, 2022
3. A promising contender for developing nano-electronic devices.30,300,50,500-tetrabromophenolsulfonphthalein (BPB) under UV-visible light irradiation, Tibebu Alemu, Gutema Taye, Girmaye Asefa, Lemessa B. Merga, *Heliyon*, 2022
4. Synthesis of Polyaniline Supported CdS/CdS-ZnS/CdS-TiO₂ Nanocomposite for Efficient Photocatalytic Applications Nida Qutub, Preeti Singh, Suhail Sabir, Khalid Umar, Suresh Sagadevan, and Won-Chun Oh, *Nanomaterials*, 2022
5. S. Novel POT/CdSe blend for optoelectronic applications K. A. Mohammed, K. M. Ziadab, A. S. AL-Kabbi, R. S. Zabibah, *Chalcogenide Letters*, 2022
6. Effect of Ultrasonic Irradiation Treatment on the Composites of Polyaniline/Cadmium Sulfide, Ravi V. Ingle, Jupinder Kaur, Prasad E. Lokhande, Vilas A. Tabhane and Habib M. Pathan, *ES Materials and Manufacturing*, 2022
7. A Review on Polyaniline: Synthesis, Properties, Nanocomposites, and Electrochemical Applications Abdulwahhab H. Majeed, Leqaa A. Mohammed, Omar G. Hammoodi, Shankar Sehgal, Mustafa A. Alheety, Kuldeep K. Saxena, Safaa A. Dadoosh, Israa K. Mohammed, Mustafa M. Jasim, and N. Ummal Salmaan, *Hindawi International Journal of Polymer Science*, 2022
8. Electrical properties of Cadmium Sulfide quantum dots and polyaniline-based nanocomposites Akhtar Rasool, Tasneem Zahra Rizvi, Sana Nayab, Zafar Iqbal, *Journal of Alloys and Compounds*, 2022
9. Polyaniline/Ag₂S–CdS Nanocomposites as Efficient Electrocatalysts for Triiodide Reduction in Dye-Sensitized Solar Cells Meng Kuo, Tsung-Chia Cheng, Huai-Kai Ye, Tzong-Liu Wang, Tzu-Ho Wu, Chi-Ching Kuo 4 and Rong-Ho Lee, *Catalysts*, 2021
10. Synthesis and Application of Nanocomposite Reinforced with Decorated Multi Walled Carbon Nanotube with Luminescence Quantum Dots Jassim Hosny Al Dalaeen, Yashfeen Khan, Anees Ahmad, *Advances in Nanoparticles*, 2021
11. Application of Magnetic Nano Particles and their Composites as Adsorbents for Waste Water Treatment: A Brief Review Meenakshi Dhiman, Baljinder Kaur, and Balwinder Kaur, *Materials Research Foundations*, 2021
12. Synthesis, D.C. Electrical Conductivity and Activation Energy of Metal Sulphides Doped Polyaniline-Nanocomposite Bhaiswar JB, Meghe DP, Salunkhe MY and Dongre SP, *Der Pharma Chemica*, 2020
13. Chemical Synthesis and Characterization of Conducting Polyaniline Salah Abdulla Hasoon, Sally Adel Abdul-Hadi, *Baghdad Science Journal*, 2020
14. Electrical properties of polyaniline/Cadmium Oxide/ZnO Nanocomposites Thin Films

- Jakeer Husain, Rehana Anjum , Shivaraj.G, Gavisiddayya.Mathad, Deepa Pathar, Jaisheel Sagar, Bushara Anjum, International Research Journal on Advanced Science Hub, 2020
15. Cadmium sulphide nanoparticles-assisted intimate coupling of microbial and photo electrochemical processes: Mechanisms and environmental applications, Guowen Dong , Honghui Wang, Zhiying Yan, Jing Zhang, Xiaoliang Ji, Maozi Lin, Randy A. Dahlgren, Xu Shang, Minghua Zhang, Zheng Chen, Science of the Total Environment, elsevier, 2020
 16. Electrical properties of Cadmium Sulfide quantum dots and Copper ferrite-Polyaniline Nanocomposite and its application for Cr (VI) ion removal from aqueous solution N.B. Singha,b, Km Rachna, Environmental Nanotechnology, Monitoring & Management, 2020
 17. Polyaniline supported CdS/CeO₂/Ag₃PO₄ Nanocomposite: An “A-B” type tandem n-n heterojunctions with enhanced photocatalytic activity Abi M. Taddesse, Tigabu Bekele, Isabel Diaz, Abebaw Adgo, Journal Pre-proof, 2020
 18. Synthetic route of PANI (II): Enzymatic method Narendra Pal Singh Chauhan, Masoud Mozafari, Synthetic route of PANI (II): Enzymatic method, 2019
 19. Cd²⁺ substituted nickel ferrite doped polyaniline nanocomposites as effective shield against electromagnetic radiation in X-band frequency Monika Saini, Rajni Shukla, Ashok Kumar, Journal of Magnetism and Magnetic Materials, 2019
 20. Tailoring the properties of polyaniline’s/SiC nanocomposites by engineering monomer and chain substituents F. Z. Kouidri, R. Berenguer, A. Benyoucef, E. Morallon, Accepted Manuscript, 2019
 21. Recent advancement in synthesis and properties of Polyaniline Nirmala Kumari Jangid, International Journal of Innovative Research in Science, Engineering and Technology, 2019
 22. Structural Analysis and Enhanced Optoelectronic Properties of PIn/CdS Nanocomposite Ajeet Verma, Ram Bilash Choudhary and Gobind Mandal, 3rd International Conference on Condensed Matter and Applied Physics, 2019
 23. CdSe Reinforced Polyaniline Nanocomposites as Superior Material for Future Applications as Gas Sensor and Diodes Rashmi Singh, Ashwani Kumar Shrivastava, and Anil Kumar Bajpai, Author Submitted Manuscript, 2019
 24. Estimation of structural and mechanical properties of Cadmium Sulfide/ PVA nanocomposite films Jammula Koteswararao, Suggala Venkata Satyanarayana, Gattumane Motappa Madhu, Vuppala Venkatesham, Heliyon, 2019
 25. Polyaniline/metal oxides nanocomposites Payam Zarrintaj, Reza Khalili, Henri Vahabi, Mohammad Reza Saeb, Mohammad Reza Ganjali, Masoud Mozafari, Fundamentals and Emerging Applications of Polyaniline, 2019
 26. Estimation of structural and mechanical properties of Cadmium Sulphide/ PVA nanocomposite films Jammula Koteswararao, Suggala Venkata Satyanarayana, Gattumane Motappa Madhu, Vuppala Venkatesham, Heliyon, 2019
 27. Functionalized polyaniline and composites Narendra Pal Singh Chauhan, Fundamentals and Emerging Applications of Polyaniline, Research Article, 2019
 28. Application of polyaniline and its derivatives Payam Zarrintaj, Henri Vahabi, Mohammad Reza Saeb, Masoud Mozafari, Fundamentals and Emerging Applications of Polyaniline, 2019
 29. Estimation of structural and mechanical properties of Cadmium Sulfide/ PVA nanocomposite films Jammula Koteswararao, Suggala Venkata Satyanarayana, Gattumane

Motappa Madhu, Vuppala Venkatesham, Heliyon, 2019

30. Augmented structural, optical and electrical properties of CdS decorated PANI/rGO nano-hybrids, Ram Bilash Choudhary, Ajeet Verma, Optical Materials, Elsevier, 2019
31. Synthesis of Titania Wrapped Cadmium Sulfide Nanorods for Photocatalytic Hydrogen Generation V. Navakoteswara Rao, N. Lakshmana Reddy, M. Mamatha Kumari, P. Ravi, Accepted Manuscript, 2018
32. Nano-adsorbents based on conducting polymer nanocomposites with main focus on polyaniline and its derivatives for removal of heavy metal ions/ dyes: A review, Ehsan Nazarzadeh Zare, Ahmad Motahari, Mika Sillanpää, Environmental Research, elsevier, 2018
33. Plasmonic polyaniline/gold nanorods hybrid composites for selective NIR photo detection: Synthesis and characterization, Gaser N. Abdelrasoul, Francesca Pignatelli, Ioannis Liakos, Roberto Cingolani, Athanassia Athanassiou, Accepted Manuscript, 2018
34. Synthesis and dielectric relaxations in self-assembled Cadmium Sulphide nanorods dispersed in conducting polymer Kousik Dutta, International Journal of Advanced Scientific Research and Management, 2018
35. Investigations on Structural and Electrical Properties of Polyaniline–Cadmium Sulphide Nanocomposite Films for Solid State Electronics Syed Khasim, Mohana Lakshmi, Hind-Al- Johani, Nacer Badi, Aashish S Roy, Polymer Composites, 2018